

# CHEMICAL RESISTANCE PROPERTIES OF SAINT-GOBAIN TUBING

The ratings in the charts on pages 1 to 3 are based on the results of laboratory tests. They reflect the relative capabilities of various Saint-Gobain Performance Plastics' tubing formulations to withstand specific chemicals. NOTE: The ratings in the charts DO NOT reflect the extent to which extraction may occur, or the extent to which fluids may undergo any physical changes in properties or composition, as a result of coming into contact with the tubing. Saint-Gobain Performance Plastics and WELCO make no representation or warranty with respect to the susceptibility of any fluid to become contaminated or undergo changes in properties or composition as a result of possible extraction of tubing ingredients by the fluid to be transmitted. Certain corrosives that would be destructive to tubing with prolonged exposure can be satisfactorily handled for short periods of time if flushed with water after use. All ratings are based on room temperature (73°F). Chemical resistance will be adversely affected by elevated temperatures. IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses, including establishing the compatibility of any fluid with the tubing through which it is transmitted. Laboratory, field or clinical tests must be conducted in accordance with applicable requirements in order to determine the safety and effectiveness for use of tubing in any particular application. If intended for medical use, it is the user's responsibility to ensure that the tubing to be used complies with all applicable medical regulatory requirements.

\* If concentration is not indicated, assume 100% concentration or the maximum percent solubility in water.

NOTE: Concentrations of room temperature liquids are given in % volume. Concentrations of room temperature solids are given in % weight.

KEY		Versilon® 2001							Versilon® 2001							
		Tygon® E-XL-60	Tygon® E-LFL	PharMed® BPT	Tygon® 3350/3355	Tygor® A-60-G	Tygor® A-60-F	Versilon® F-5500-A	Benzaldehyde	Tygon® E-XL-60	Tygon® E-LFL	PharMed® BPT	Tygon® 3350/3355	Tygor® A-60-G	Tygor® A-60-F	Versilon® F-5500-A
Acetaldehyde	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Acetamide, 67% in w	G	G	X	G	E	G	G	G	X	X	X	X	X	X	X	X
Acetate Solvents	X	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Acetic Acid, 10% in w	G	E	E	E	E	E	E	E	X	X	X	X	X	X	X	X
Acetic Acid, 50-60% in w	E	E	E	G	E	G	G	G	X	X	X	X	X	X	X	X
Acetic Acid, Glacial, 100%	G	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Acetic Anhydride	E	E	X	E	E	E	E	E	X	X	X	X	X	X	X	X
Acetone	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Acetonitrile	G	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Acetyl Bromide	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Acetylene Chloride	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Acetylene Gas	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Acrylonitrile	G	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Adipic Acid, 100% in alc	G	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Air	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Alcohols General	E	X	X	E	G	E	E	E	X	X	X	X	X	X	X	X
Aliphatic Hydrocarbons	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Allyl Alcohol	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Alum, 5% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Aluminum Chloride, 53% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Aluminum Hydroxide, 2% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Aluminum Salts	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Aluminum Sulfate, 50% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Amines	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Ammonia Gas	E	E	E	E	X	E	E	E	X	X	X	X	X	X	X	X
Ammonia, Anhydrous Liquid	G	E	G	E	X	G	G	G	X	X	X	X	X	X	X	X
Ammonium Acetate, 45% in w	E	E	E	E	E	E	E	E	E	X	X	X	X	X	X	X
Ammonium Carbonate, 50% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Ammonium Hydroxide, 30% in w	E	E	E	E	X	E	E	E	X	X	X	X	X	X	X	X
Ammonium Hydroxide, 5-10% in w	E	E	E	E	X	E	E	E	X	X	X	X	X	X	X	X
Ammonium Persulfate, 30% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Ammonium Salts	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Ammonium Sulfate, 30% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Amyl Acetate	X	X	X	G	X	G	G	G	X	X	X	X	X	X	X	X
Amyl Alcohol	E	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Amyl Chloride	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Aniline	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Aniline Hydrochloride	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Antimony Salts	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Aqua Regia	E	E	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Aromatic Hydrocarbons	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Arsenic Acid, 20% in w	E	X	E	X	X	X	X	X	E	X	X	E	E	E	E	E
Arsenic Salts	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
ASTM Reference No.1 Oil	X	X	X	X	E	X	X	X	E	X	X	E	E	E	E	E
ASTM Reference No.2 Oil	X	X	X	X	G	X	X	X	E	X	X	E	E	E	E	E
ASTM Reference No.3 Oil	X	X	X	X	X	X	X	X	X	X	X	E	E	E	E	E
Barium Carbonate, 1% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Barium Hydroxide, 5% in w	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
Beer	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E

KEY  
 E Excellent  
 G Good  
 X Not Recommended  
 Environment, % Conc.\*  
 w-Water alc-Alcohol

	<i>Version® 2001</i>	<i>Tygon® XL-60</i>	<i>TygonS3® E-LFL</i>	<i>PharMed® BPT</i>	<i>Tygon® 3350/3355</i>	<i>Tygon® A-60-G</i>	<i>Tygon® A-60-F</i>	<i>Version® E-5500-A</i>
Dibutyl Phthalate	E	X	X	E	E	E	E	E
Diesel Fuel	X	X	X	X	X	X	X	E
Diethylamine, 2.5% in w	E	E	E	E	X	E	E	X
Diethylene Glycol	E	E	E	E	E	E	E	E
Dimethylformamide	E	E	X	G	E	G	G	X
Dimethylsulfoxide	E	X	X	E	X	E	E	X
Diocyl Phthalate	E	X	X	E	E	E	E	E
Dioxane	X	X	X	X	X	X	X	X
Ether	X	X	X	X	X	X	X	X
Ethyl Acetate	X	E	X	G	X	G	G	X
Ethyl Alcohol (Ethanol)	E	E	X	X	X	X	X	X
Ethyl Benzoate	X	X	X	X	X	X	X	X
Ethyl Chloride	X	E	X	X	X	X	X	X
Ethyl Ether	X	X	X	X	X	X	X	X
Ethylene Bromide	X	X	X	X	E	X	X	E
Ethylene Chlorhydrin	E	E	X	E	G	E	E	X
Ethylene Dichloride	X	E	X	X	X	X	X	X
Ethylene Glycol	E	E	E	E	E	E	E	E
Ethylene Oxide	E	E	E	E	E	E	E	E
Fatty Acids	X	E	X	X	G	X	X	E
Ferric Chloride, 43% in w	E	E	E	E	E	E	E	E
Ferric Nitrate, 60% in w	E	E	E	E	E	E	E	E
Ferric Sulfate, 5% in w	E	E	E	E	E	E	E	E
Ferrous Chloride, 40% in w	E	E	E	E	E	E	E	E
Ferrous Sulfate, 5% in w	E	E	E	E	E	E	E	E
Fluoboric Acid, 48% in w	E	E	X	X	X	X	X	E
Fluorine Gas	X	X	X	X	X	X	X	G
Fluosilicic Acid, 25% in w	E	E	E	X	X	X	X	E
Formaldehyde, 37% in w	X	E	X	X	X	X	X	X
Formic Acid, 25% in w	E	E	E	E	E	E	E	E
Formic Acid, 40-50% in w	E	E	G	G	E	G	G	X
Formic Acid, 98% in w	E	E	X	G	E	G	G	X
Freon 11	E	G	E	E	E	E	E	G
Freon 12	E	G	E	E	E	E	E	G
Freon 22	E	G	E	E	E	E	E	G
Fruit Juice	E	E	E	E	E	E	E	E
Fuel Oil	X	X	X	X	X	X	X	E
Furfural	X	X	X	X	X	X	X	X
Gallic Acid, 17% in acetone	X	X	X	G	X	G	G	X
Gasoline, Automotive	X	X	X	X	X	X	X	E
Gelatin	E	E	E	E	E	E	E	E
Glucose, 50% in w	E	E	E	E	E	E	E	E
Glycerol (Glycerin)	E	E	E	E	E	E	E	E
Glycolic Acid, 70% in w	E	G	E	G	E	G	G	X
Heptane	X	X	X	X	X	X	X	G
Hexane	X	X	X	X	X	X	X	G
Hydrazine	X	X	X	X	X	X	X	X
Hydrobromic Acid, 100% in w	E	E	X	X	X	X	X	E
Hydrobromic Acid, 20-50% in w	E	E	E	X	X	X	X	E
Hydrochloric Acid, 10% in w	E	E	E	E	E	E	E	E
Hydrochloric Acid, 37% in w	E	E	X	G	X	G	G	G
Hydrocyanic Acid	E	E	E	E	E	E	E	X
Hydrofluoric Acid, 10% in w	E	E	E	X	X	X	X	E
Hydrofluoric Acid, 25% in w	E	E	X	X	X	X	X	E
Hydrofluoric Acid, 40-48% in w	E	E	X	X	X	X	X	E
Hydrogen Gas	E	E	E	E	E	E	E	E
Hydrogen Peroxide, 10% in w	E	E	E	E	E	E	E	E
Hydrogen Peroxide, 3% in w	E	E	E	E	E	E	E	E
Hydrogen Peroxide, 30% in w	E	E	E	E	E	E	E	E
Hydrogen Peroxide, 90% in w	G	E	X	G	X	G	G	E
Hydrogen Sulfide	E	E	E	E	E	E	E	E
Hydroquinone, 7% in w	E	G	E	G	G	G	G	E
Hypochlorous Acid, 25% in w	E	E	E	E	E	E	E	E

	<i>Version® 2001</i>	<i>Tygon® XL-60</i>	<i>TygonS3® E-LFL</i>	<i>PharMed® BPT</i>	<i>Tygon® 3350/3355</i>	<i>Tygon® A-60-G</i>	<i>Tygon® A-60-F</i>	<i>Version® E-5500-A</i>
Iodine, 50ppm in w	E	E	E	E	E	E	E	E
Isobutyl Alcohol	E	X	X	X	X	X	X	E
Isooctane	X	X	X	X	X	X	X	E
Isopropyl Acetate	X	X	X	G	X	G	G	X
Isopropyl Alcohol	E	X	X	X	X	X	X	E
Isopropyl Ether	E	X	E	X	X	X	X	X
IsopropylAlcohol	E	E	X	X	X	X	X	E
Jet Fuel, JP8	X	X	X	X	X	X	X	E
Kerosene	X	X	X	X	X	X	X	E
Ketones	X	X	X	X	X	X	X	X
Lacquer Solvents	X	X	X	G	X	G	G	X
Lactic Acid, 3-10%(w)	E	E	E	E	E	E	E	X
Lactic Acid, 85%(w)	E	E	X	G	X	G	G	X
Lard,Animal Fat	G	X	X	E	X	X	X	E
Lead Acetate, 35%(w)	E	E	E	E	E	E	E	E
Lead Salts	E	E	E	E	E	E	E	E
Lemon Oil	X	X	X	X	X	X	X	E
Limonene-D	X	X	X	X	X	X	X	E
Linoleic Acid	X	X	X	X	G	X	X	E
Linseed Oil	G	X	X	X	E	X	X	E
Lubricating Oils, Petroleum	X	X	X	X	G	X	X	E
Magnesium Carbonate, 1% in w	E	E	E	E	E	E	E	E
Magnesium Chloride, 35% in w	E	E	E	E	E	E	E	E
Magnesium Hydroxide, 10% in dil. Acid	E	E	E	E	E	E	E	E
Magnesium Nitrate, 50% in w	E	E	E	E	E	E	E	E
Magnesium Sulfate, 25% in w	E	E	E	E	E	E	E	E
Maleic Acid, 30% in w	X	X	X	X	G	X	X	E
Manganese Salts	E	E	E	E	E	E	E	E
Mercuric Chloride, 6% in w	E	E	E	E	E	E	E	E
Mercuric Cyanide, 8% in w	E	E	E	E	E	E	E	E
Mercury	E	E	E	E	E	E	E	E
Mercury Salts	E	E	E	E	E	E	E	E
Methane Gas	E	E	E	E	E	E	E	E
Methyl Acetate	X	X	X	G	X	G	G	X
Methyl Bromide	X	X	X	X	X	X	X	X
Methyl Chloride	X	X	X	X	X	X	X	X
Methyl Ethyl Ketone	X	X	X	X	X	X	X	X
Methyl Isobutyl Ketone	X	X	X	X	X	X	X	X
Methyl Methacrylate	X	X	X	X	X	X	X	X
Methylene Chloride	X	X	X	X	X	X	X	X
Milk	E	E	E	E	E	E	E	E
Mineral Oil	X	X	X	X	X	X	X	E
Mineral Spirits	X	X	X	X	X	X	X	E
Monoethanolamine	X	E	X	X	X	X	X	X
Motor Oil	X	X	X	X	X	X	X	E
Naphtha	X	X	X	X	X	X	X	E
Naphthalene	X	X	X	X	X	X	X	E
Natural Gas	E	E	E	E	E	E	E	E
Nickel Chloride, 40% in w	E	E	E	E	E	E	E	E
Nickel Nitrate, 75% in w	E	E	E	E	E	E	E	E
Nickel Salts	E	E	E	E	E	E	E	E
Nickel Sulfate, 25% in w	E	E	E	E	E	E	E	E
Nitric Acid, 10% in w	E	E	E	E	E	E	E	E
Nitric Acid, 35% in w	E	E	G	E	X	E	E	X
Nitric Acid, 68-71% in w	E	E	X	X	X	X	X	X
Nitrobenzene	X	X	X	X	X	X	X	X
Nitromethane	X	X	X	X	X	X	X	X
Nitrous Acid, 10% in w	E	E	E	E	X	E	E	E
Nitrous Oxide	E	E	E	E	E	E	E	E
Oils, Animal	G	X	X	X	E	X	X	E
Oils, Hydraulic (Phosphate Ester)	X	X	X	X	X	X	X	E
Oils, Hydrocarbon	X	X	X	X	G	X	X	E
Oils, Vegetable	G	X	X	X	E	X	X	E

	<i>Versilon® 2001</i>	<i>Tygon® XL-60</i>	<i>TygonS3® E-LFL</i>	<i>PharMed® BPT</i>	<i>Tygon® 3330/3355</i>	<i>Tygon® A-60-G</i>	<i>Tygon® A-60-F</i>	<i>Versilon® F-5500-A</i>	<i>Versilon® 2001</i>	<i>Tygon® XL-60</i>	<i>TygonS3® E-LFL</i>	<i>PharMed® BPT</i>	<i>Tygon® 3330/3355</i>	<i>Tygon® A-60-G</i>	<i>Tygon® A-60-F</i>	<i>Versilon® F-5500-A</i>
KEY									KEY							
E Excellent									G Excellent							
G Good									E Good							
X Not Recommended									X Not Recommended							
Environment, % Conc.*									Environment, % Conc.*							
w-Water alc-Alcohol									w-Water alc-Alcohol							
Oils, Essential	X	X	X	X	X	X	X	E	Sulfur Trioxide, Wet	G	E	G	G	G	G	G
Oleic Acid	X	X	X	X	G	X	X	E	Sulfuric Acid, 10% in w	E	E	E	E	E	E	E
Oleum, 25% in w	E	G	E	E	G	E	E	E	Sulfuric Acid, 30% in w	E	E	E	G	E	E	E
Ortho Dichlorobenzene	X	X	X	X	X	X	X	X	Sulfuric Acid, 95-98% in w	X	E	X	X	X	X	E
Oxalic Acid, 12% in w	E	E	X	G	E	G	G	X	Sulfurous Acid	E	E	E	E	E	E	E
Oxygen	E	E	E	E	E	E	E	E	Tannic Acid, 75% in w	E	E	X	G	E	G	X
Ozone, 300pphm	E	E	E	E	E	E	E	E	Tartaric Acid, 56% in w	E	E	E	E	E	E	E
Palmitic Acid, 100% in ether	X	X	X	X	G	X	X	E	Tetrahydrofuran	X	X	X	X	X	X	X
Paraffins	X	X	X	X	X	X	X	G	Thionyl Chloride	E	E	E	E	E	E	E
Perchloric Acid, 67% in w	E	E	X	E	X	E	E	E	Tin Salts	E	E	E	E	E	E	E
Perchloroethylene	X	X	X	X	X	X	X	X	Titanium Salts	E	E	E	E	E	E	E
Phenol, 5-10% in w	E	X	G	E	E	E	E	E	Toluene	X	X	X	X	X	X	X
Phenol, 91% in w	E	X	X	E	G	E	E	E	Trichloroacetic Acid, 90% in w	E	E	E	G	E	G	X
Phosphoric Acid, 10% in w	E	E	E	E	X	E	E	E	Trichloroethane	X	X	X	X	X	X	X
Phosphoric Acid, 25% in w	E	E	E	E	X	E	E	E	Trichloroethylene	X	X	X	X	X	X	X
Phosphoric Acid, 85% in w	E	G	E	E	X	E	E	E	Trichloropropane	X	X	X	X	X	X	X
Phosphorous Trichloride Acid	E	G	E	G	X	G	G	G	Tricresyl Phosphate	E	E	X	E	E	E	E
Photographic Solutions	E	G	E	G	G	G	G	E	Triethanolamine	X	X	X	X	X	X	X
Phthalic Acid, 9% in alc	E	X	X	E	G	E	E	E	Trisodium Phosphate	E	E	E	E	E	E	E
Phthalic Anhydride, 9% in alc	E	G	X	E	E	E	E	X	Turpentine	X	X	X	X	X	X	E
Picric Acid, 1% in w	E	X	E	X	X	X	X	E	Urea, 20% in w	E	E	E	E	E	E	E
Plating Solutions	E	G	E	E	X	E	E	E	Uric Acid	E	E	E	E	E	E	X
Potassium Carbonate, 55% in w	E	E	E	E	E	E	E	E	Vinegar	E	E	E	E	E	E	X
Potassium Cyanide, 33% in w	E	E	E	E	E	E	E	E	Vinyl Acetate	X	X	X	G	X	G	X
Potassium Dichromate, 5% in w	E	E	E	E	E	E	E	E	Water, Deionized	E	E	E	E	E	E	E
Potassium Hydroxide, 10% in w	E	E	E	E	E	E	E	E	Water, Distilled	E	E	E	E	E	E	E
Potassium Hypochlorite, 70% in w	E	G	E	E	E	E	E	E	Xylene	X	X	X	X	X	X	X
Potassium Iodide, 56% in w	E	E	E	E	E	E	E	E	Zinc Chloride, 80% in w	E	E	E	E	E	E	E
Potassium Permanganate, 6% in w	E	E	E	E	E	E	E	E	Zinc Salts	E	E	E	E	E	E	E
Potassium Salts	E	E	E	E	E	E	E	E								
Propane Gas	E	E	E	E	E	E	E	E								
Propylene Glycol	E	E	E	E	E	E	E	E								
Propylene Oxide	E	E	E	E	E	E	E	E								
Pyridine	X	E	X	X	X	X	X	X								
Salicylic Acid, 1% in w	E	E	E	E	E	E	E	X								
Silicone Oils	G	E	G	X	X	X	X	E								
Silver Nitrate, 55% in w	E	E	E	E	E	E	E	E								
Skydrol 500A	X	X	X	X	X	X	X	E								
Soap Solutions	E	E	E	G	E	G	G	E								
Sodium Acetate, 55% in w	E	E	E	E	E	E	E	E								
Sodium Benzoate, 22% in w	E	E	E	E	E	E	E	E								
Sodium Bicarbonate, 7% in w	E	E	E	E	E	E	E	E								
Sodium Carbonate, 7% in w	E	E	E	E	E	E	E	E								
Sodium Chlorate, 45% in w	E	E	E	E	E	E	E	E								
Sodium Chloride, 20% in w	E	E	E	E	E	E	E	E								
Sodium Cyanide, 30% in w	E	E	E	E	E	E	E	E								
Sodium Fluoride, 3% in w	E	E	E	E	E	E	E	E								
Sodium Hydroxide, 10-15% in w	E	E	E	E	E	E	E	E								
Sodium Hydroxide, 30-40% in w	E	E	G	E	E	E	E	E								
Sodium Hypochlorite, 12.2% in w	E	E	X	E	X	E	E	E								
Sodium Hypochlorite, 5.5% in w	E	E	E	E	X	E	E	E								
Sodium Nitrate, 3.5% in w	E	E	E	E	E	E	E	E								
Sodium Salts	E	E	E	E	E	E	E	E								
Sodium Sulfate, 5% in w	E	E	E	E	E	E	E	E								
Sodium Sulfide, 45% in w	E	E	E	E	E	E	E	E								
Sodium Sulfite, 10% in w	E	E	E	E	E	E	E	E								
Stannic Chloride, 50% in w	E	E	E	E	E	E	E	E								
Stannous Chloride, 45% in w	E	E	E	E	E	E	E	E								
Stearic Acid, 5% in alc	X	E	X	X	G	X	X	E								
Styrene Monomer	X	X	X	X	X	X	X	X								
Sulfur Chloride	E	E	X	X	X	X	X	X								
Sulfur Dioxide, Gas Dry	E	E	E	E	E	E	E	E								
Sulfur Dioxide, Gas Wet	E	E	E	E	E	E	E	E								